



# ADBIT-R

adhesive additives for road bitumen

TU U 30309233.001-2000

---

Improving the properties of road bitumen by introducing an adhesive additive "ADBIT-R" in the conditions of asphalt plant is carried out using the following technologies:

1. Dehydrated bitumen in the bitumen is heated to a temperature **125-180 ° C**.
2. The adhesive additive "ADBIT-R" 'is dispensed into the boiler manually or automatically in an amount of **0.25-0.4%** by weight of bitumen.
3. Stirring may be of bitumen pump ("on itself") or any other mechanical means.
4. The mixing time is determined experimentally verify the change of indicators of quality in the preparation of the binder.